

IDROFUGHE 2K

Kind: Dispersing elastic

Product:

IDROFUGHE 2K is a cement mortar at high performances, modify with the polymers for the grouting up to 6 mm.

Application fields:

Inside and outside grouting of floors and ceramics coating of every kind.

Preparation of the supports:

Before to start the grouting of the grouts wait that the mortar lodging or that the adhesive are completely dry/hard. The grouts must be clean, dust free and empty for at least 2/3 of the tiles thickness.

Application methods:

Pour IDROFUGHE 2K, while stirring, into a clean container and containing clean water in a quantity rate about 24% of the weight. Mix with a drill with a low laps number to avoid an excessive incorporation of air in the mix, up to achieving a homogeneous mix and lump free. Use the mix within 2 hours from the preparation.

Fill the leaks with the mix IDROFUGHE 2K using the appropriate rubber spatula without leaving any emptiness or gradients. Remove the excess from the surface moving the spatula diagonally to leaks to mix still fresh.

When the dough loses its elasticity and become opaque, usually after 10 – 20 minutes, clean the residue with a wet sponge.

The floors are walkable after about 24 hours.

Technical data:

- | | |
|------------------------|--|
| • Packaging | bag of 25 Kg |
| • Colour | cement grey |
| • Mixing with water | 24% |
| • Dough density | about 2.000 Kg / m ³ |
| • Mix duration at 20°C | 2 hours |
| • Walkability | 36 hours |
| • Consumption | depends on the shape of the tile and the kind of grout |

Please note:

The information and the prescriptions above reported, even reflecting to our experience, are to be considered, in any way, purely indicative and have to be confirmed from comprehensive practical applications; therefore, before using the product, who is intentioned to use it, is required to determinate whether it is or is not suitable for the planned use and anyway takes every responsibility that may arise from its use.